

SANI-CARE PHYSICAL PROPERTIES

Data from Espoma Testing Laboratory

Sani-Care bedding is derived from microcube cut birch, beech or maple wood species and obtained from sustainable managed forests. It is free of shavings, slivers and all foreign matter. It is virtually dust free.

Density 13 lbs/ft³ +/- 2lbs varies with blend of wood species which is why it is sold by volume

Sizing	USA Standard Test Sieve Size (ASTM E-11)	% Retained on Screen
	16	0
	20	30
	25	25
	30	20
	40	8
	> 40	2

Heat Treatment 1200° F for minimum of 20 minutes

Moisture Content 8% +/- 2%

Absorptivity > 300% by weight

Relative Absorption % Moisture Absorbed

Pine Shavings 25%

Pine Flakes 35%

Sani-Care 100%